



# Technical Data Sheet

6/2/2006

Product: **4300**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Pink	
Density (lbs / ft3)	1.15 - 1.35	ASTM D-3574-01
Indent Force Deflection @ 25%	32 - 38	ASTM D-3574-01
Compression Set at 50% comp.(%)	10	ASTM D-3574-01
Tensile Strength (psi)	12	ASTM D-3574-01
Tear Strength (lbs/lin inch)	1.2	ASTM D-3574-01
Elongation (%)	100	ASTM D-3574-01
Flame Resistance	N/A	
Static Decay	2.0 seconds max	FTMS 101C; Method 4046
Surface Resistivity	$\sim 10^{11}$ ohms/square	ASTM D-257

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Amcon does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.

**WARNING: URETHANE FOAM IS FLAMMABLE!**  
**Urethane Foam should not be exposed to open flame or other ignition sources.**  
**Urethanes burn rapidly with great heat and release gases which are extremely hazardous.**

5360 Main St. NE Minneapolis, MN 55421

Ph. 888-360-8050

**[www.amconfoam.com](http://www.amconfoam.com)**